


	NATURAL SALT SPRAY REPORT (Test Conducted as per ASTM B 117)			Doc. No. EFFCO/19-20	
				TC DATE: 09-07-2021	
				Page 1 of 1	
SST Batch No.	90	Customer Name	Self		
Components Name/No.	Bolts	Colour	Silver	No. of Samples	2
Coating System	Zinc Al flake coating	Coating / Product used	Ecomet 500 LC + Ecomet Top Clear B		
Coating Process	Dip Spin Coating	No.of Coat	2 Base	1 Top	
Coating Thickness	8-10 micron	SST Equipments	Corrosion Test Appratus AS per ASTM B117		
Component Loaded for SST on Date & time	24/05/2021 4.30 PM	Customer Requirement for SST in hours	72 Hours - No Red Rust		
Test Stop Date & Time	08/07/2021 2.00 pm	Observation for Red Rust	NO Red Rust Observed after 1200 Hrs.		
SAMPLE PHOTO BEFORE SST			SAMPLE PHOTO AFTER SST		
					
Remark: OK					

Checked and approved by:

A handwritten signature in black ink, appearing to be 'J. M. L.', is written over a horizontal line.