

PRODUCT DATA SHEET

ECOMET TOP GREEN

These Organic topcoats can be applied over Zinc plating and Zinc/Aluminium flake-based Basecoats. Application techniques can be used as Dip-Spin for mass produced small hardware's, Screws and Conventional spray for larger parts.

PHYSICAL PROPERTIES	Units	
Colour		Green
Theoretical coverage	m ² /kg/10 μ	15 - 20
Viscosity (Zhan Cup 2)	Seconds	40 - 50
Solids (By Weight)	%	33 ± 3
Density	Gms/cc	1.10 +/- 0.1
Flash point	°C	>100
COF Values ISO 16047	μ _{tot}	0.12 - 0.18
Chrome Content		N.A.

APPLICATION

Substrate	Any metal substrate except high copper containing alloys.
Surface preparation	The substrate must be dry and free from dust and grease. Acidic/ basic impurities and particularly salts must be avoided.
Possible Pre-treatment / Basecoat	Zinc/Al flake-based Basecoats, Electroplating etc.
Application Method	Dip / Spin, Dip, Spray etc.
Filtration	150 mesh stainless steel sieve
Application viscosity	25 - 30 sec. on Zhan cup 2 for Dip-spin & 18 - 20 for Spray application.
Recommended DFT	8-12 μ
Addition	DM Water
Addition of DM Water	5 - 10 % by weight
Flash Off	5-10 min. at 100-120°C.
Curing (metal temp.)	25 - 30 min. at 200 - 220 °C

- Physical constants are averages and are not to be used as product specifications. They may vary up to 5 % of the values shown are specifications representative for the process capability.

-Storage life is 12 months at 20-25°C. For more information on health & safety refer Material safety data sheet for handling and applying

SUMMMARY

ECOMET TOP GREEN

Coating Test

Recommended Base Coat:

- Acid Zinc Plating
- Alkaline Zinc Plating
- ECOMET Corundum
- ECOMET 500

PHYSICAL TESTS OF LIQUID PAINT

#	Name of Test	Procedure	Results	Comment
1.	Viscosity	By Zhan Cup no. 2	40 - 50 seconds	
2.	Solid Content	By weight	33 % +/- 3	
3.	pH	pH meter	8 - 9	

AFTER APPLICATION ON SUBSTRATE: PHYSICAL TESTS

#	Name of Test	Procedure	Results	Comment
1.	Coating Layer Thickness		6 - 8 Micron	By Thickness gauge
2.	Adhesion	ISO-10683	Pass	7Nm/12mm ²
3.	Hardness of Film	Pencil Test	> 4 H	

AFTER APPLICATION ON SUBSTRATE: CHEMICAL TESTS

#	Name of Test	Procedure	Results	Comment
1.	Automotive Oil and Fuel Tests	Dip	Pass	
2.	Acid test – 2PH	Dip	Pass (30 Seconds)	

AFTER APPLICATION ON SUBSTRATE: PERFORMANCE TESTS

#	Name of Test	Procedure	Results	Comment
1.	SST	ASTM B117	500 Hours	Additional to Basecoat
2.	COF Test	ISO16047	0.15 +/- 0.03 tot	Others on request

Disclaimer: The information given herewith is provided in good faith and is based on internal information. The performance may vary from customer to customer. Effco makes no warranties, expressed, or implied as to the accuracy of the information. Effco disclaims liability for any incidental or consequential damage. These data & information cannot be taken for any legal claim or court procedure. Lab trials should be conducted before taking bulk batch.